

LIGHT 110

LIGHTWEIGHT POLYESTER PUTTY

High quality lightweight polyester putty, designed for bodyshops with excellent filling capacity.

PRODUCT

LIGHT 110

PROPERTIES

- Very light, very easy to apply, fast and excellent filling capacity.
- High performance.
- Fine homogeneous structure.
- Smooth sanding.









SUBSTRATES

- Specially recommended for bare steel, electrogalvanized steel, and fiberglass polyester.
- We recommend its coating with FILLER 220-225-229-250.

LIGHT 110

LIGHTWEIGHT POLYESTER PUTTY

PRODUCT PREPARATION

 MIXING RATIO VOLUME		Horizontal panel or mid size reparations
	PEROXIDE	Weight 2-3%
 POT-LIFE AT 20°C	PEROXIDE	4-5 min.
 APPLICATION VISCOSITY AT 20°C	FORD N°	No
 SPATULA APPLICATION		Spatula application.
 NR LAYERS		No
 THINNER EVAPORATION		No
DFT		1000-3000 microns
 DRYING TIME		Peroxide
	DRY	30 min.
 INFRARED DRYING	MIDDLE WAVE	5 min.
	SANDING	P120 – P220

LIGHT 110

LIGHTWEIGHT POLYESTER PUTTY

SURFACE PREPARATION

- Wash the surface with soap and water. Rinse and dry.
- Remove grease thoroughly with proper cleanser. Dry surface with clean cloth.
- Repair damages.
- Degrease using proper cleansing product. Dry with clean cloth.
- Make sure there are not any traces of dust.
- If necessary, apply a double-coating base.

STORAGE

Store product under cover, in a well-ventilated area, away from direct sun-light. Store at temperature between 5-30 degrees Celsius.

Duration of container 2 years. After that period, please consult our technical department.

HEALTH AND SAFETY

For Professional use Only.

KEEP AWAY FROM CHILDREN. WARNING! FLAMMABLE CONTENT.

HARMFUL VAPORS AND VOLATILE COMPOUNDS. IRRITATING TO EYES AND SKIN.

Handle CROMAUTO products only after having read and understood completely the materials security and safety information data sheets. Make sure that every employee is aware of data information sheets as well as all the chemical substances they get in contact with. The Manufacturer recommends the use of an air respirator while being exposed to the sprayed mist and vapors. Use appropriate clothing, gloves, and goggles with side shields.

The information provided in these sheets is given in good faith, but it does not constitute a guarantee. The included information represents our current knowledge and it is aimed to serve as a guide or reference of our products and their purpose, but it does not guarantee certain properties of the products nor their specific applications.

Please, respect every warning on the products labels.